




NUT, PLATE, SELF-LOCKING, LOW HEIGHT, FIXED, TWO LUG

CODE: "A" -- STEEL MATERIAL, CAD PLATE PER AMS-QQ-P-416, TYPE II, CLASS 2, MoS₂ DRY FILM LUBRICANT.
 "X" -- SAME AS "A" CODE WITHOUT DRY FILM LUBRICANT.
 "CS" -- A286 CRES MATERIAL, SILVER PLATE PER AMS2410.
 "CM" -- A286 CRES MATERIAL, MoS₂ DRY FILM LUBRICANT.
 "K" -- FOLLOWING DASH NUMBER INDICATES DIMPLED RIVET HOLES.
 "W" -- FOLLOWING DASH NUMBER INDICATES PROJECTION WELD NIBS. "CS" CODE ONLY, NO SILVER PLATE ON WELD NIBS.

EXAMPLE CALLOUT:



- NOTES:
- /1/ MINIMUM "E" LIMITED ONLY BY STRENGTH REQUIREMENTS OF SPECIFICATION.
 - /2/ THREADS SHALL BE MJ FORM IN ACCORDANCE WITH FED-STD-H28/21. FOR ACCEPTABILITY SEE PROCUREMENT SPECIFICATION.
 - (3) DIMENSIONING AND TOLERANCING PER ASME Y14.5M.
 - (4) DIMENSIONS IN MILLIMETERS AND APPLY AFTER FINISH AND PRIOR TO THE APPLICATION OF LUBRICATION UNLESS OTHERWISE SPECIFIED.
 - (5) FOR CRES, MAGNETIC PERMEABILITY SHALL BE LESS THAN 2.0 (AIR=1.0) FOR A FIELD STRENGTH H=16 kA/m USING A MAGNETIC PERMEABILITY INDICATOR PER ASTM A 342/A M, TEST METHOD 3.
 - (6) THIS STANDARD TAKES PRECEDENCE OVER DOCUMENTS REFERENCED HEREIN.
 - (7) UNLESS OTHERWISE SPECIFIED, PART INVENTORY MANUFACTURED TO PREVIOUS REVISIONS OF THE APPLICABLE DRAWING OR SPECIFICATION MAY BE PROCURED AND USED UNTIL STOCK IS DEPLETED.
 - (8) REFERENCED DOCUMENTS SHALL BE THE ISSUE IN EFFECT ON DATE OF INVITATIONS FOR BID.

PROCUREMENT SPECIFICATION:

STEEL NUTS -- NA0009 CLASS II.
 CRES NUTS -- NA0044 CLASS II.

ALL PARTS MUST MEET QUALIFICATION AND INSPECTION REQUIREMENTS. MANUFACTURERS SHALL PROVIDE EVIDENCE OF QUALIFICATION WHEN REQUIRED. TESTING SHALL BE PERFORMED BY MANUFACTURER OR INDEPENDENT LABORATORY. PROCURING AGENCY MAY CONDUCT CONFIRMING QUALIFICATION TESTS. NO QPL SHALL BE ESTABLISHED.

CONFORMS TO:
 NASM25027
 AS8879

NAFCO USA, LLC
 CARSON CITY, NV 89706

PART NUMBER
NA2452
 FSCM / CAGE CODE: 32387